

## **UNILUB - PE 7**

**UNILUB PE-7** is a low polymer polyethylene wax, obtained by polymerizing and distilling the low polymer wax obtained during polyethylene manufacturing process. We ensure that it is free from moisture, volatiles, residual impurities, so that it gives excellent colour, lubrication, stability and output when used in different applications, specially external lubrication in plastics. The flakes and snowhite and crisp in nature.

Doc. No.: UNILUB-4

Issue No.: 02

Issue Date: 17.11.2015

Replaces: Nil

## TYPICAL PHYSIOCHEMICAL PROPERTIES

| PROPERTY                                       | UNIT    | UNILUB - PE 7          |
|--|---------|------------------------|
| Appearance                                     | -       | Snow white soft flakes |
| Ash content                                    | % max   | 0.10                   |
| Drop Point (ASTM D 3954)                       | Deg C   | 112-118                |
| Hardness (ASTM D 1321)                         | -       | 5                      |
| K. Viscosity (ASTM D 3236)                     | ср      | 40-60                  |
| Moisture                                       | % max   | 1.0                    |
| Volatiles                                      | % max   | 2.0                    |
| Softening Point                                | Deg C   | 100-105                |
| Average molecular weight                       | -       | 1000-1200              |
| Thermal stability time in plasticized compound | minutes | 100                    |

This information and our technical advice-whether verbal, in writing or by way of trials are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sales and Delivery.

5) At the time of packing 5) By IR Moisture Balance 3) IS: 7589-1974 (A-8)

## **APPLICATIONS:**

- As an external lubricant in plastics processing, specially rigid PVC
- · As a multifunctional lubricant in plasticized PVC
- As a shining agent / binding agent in masterbatches and filler compounds
- · Candle application and wick coating

## **Correspondence Address:**

111/230, Harsh Nagar KANPUR - 208 012. (INDIA)

Ph. :0512-2555292

Website: www.mlagroup.com Email: info@mlagroup.com















