

ZINCOSIL RT-70

PHYSIOCHEMICAL PROPERTIES

PROPERTY	UNIT	VALUE
Surface Area (BET) ³	m ² /gm	22-26
Bulk Density ^{1,4}	gm/cc	0.6 - 0.8
Oil Absorption	%	30-40
pH (2% acq. solution) ⁵	%	7.2 - 8.8
ZnO	%	72±4
Pb, Cu, Ni, Mn, Cd	ppm max. total	20
Moisture (90°C) ²	%	<2.0
Residue on 300 mesh ⁶	%	<0.8

1) At the time of packing 2) By IR Moisture Balance 3) Determined on coulter SA 3100 Surface Area Analyzer (by Nitrogen adsorption BET method) 4) IS: 7086 (Part I) 1973 5) By Anthraquinone pink spot test

APPLICATIONS

- Suitable for following types of rubber-NR, IR, BR, SBR, IIR, CR, EPDM, CSM.
- Highly elastic vulcanizates (spring components).
- Can be used as activator in -
 1. Sulphur cures
 2. Peroxide cures (often)
 3. Sulphurless metallic-oxide cures.
 4. Used as cross-linking agent for lattices with reactive groups and for CR.

PACKING

25 kgs in new laminated H.D.P.E. bags with loose polythene liner inside.

INCORPORATION/USAGE

1. In large proportions, zinc-oxide active, NK-A behaves like reinforcing filler. It give vulcanizate high tensile strength and rebound resilience with a simultaneous increase in hardness. It also imparts resistance to ageing and protection against flex cracking.
1. Successively larger additions raise the degree of cross linkage and thus improve the mechanical properties of the vulcanizates, especially the modulus, resistance to abrasion and tearing.
2. As its proportion is increased, the thermal conductivity of rubber mixes is raised which is an advantage in hot air curing.
3. Owing to the fineness of particles, RT-70 is very easy to incorporate and disperses well.
4. It raises the viscosity of the mix. Large additions stiffen the mix considerably.

Doc. No.: Z0-05

Issue No.: 03

Issue Date: 28.06.2016

Replaces: All Previous Issues

This information and our technical advice-whether verbal, in writing or by way of trials are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sales and Delivery.

Correspondence Address :

111/230, Harsh Nagar
KANPUR - 208 012. (INDIA)
Ph. :0512-2555292
Website: www.mlagroup.com
Email: info@mlagroup.com

CERTIFICATIONS

